

RAS3/650

pulitori / scrapers



Caratteristiche della gomma / rubber characteristics

| | Um | Norme / norms | Valore / value |
|--|-------------------|---------------|----------------|
| Polimero base / base polymer | | | NR-SBR |
| Durezza / hardness | SH/A | UNI 4916 | 62 |
| Peso specifico / specific weight | g/cm ³ | UNI 7092 | 1,16 |
| Modulo a 300 % / form to 300% | MPa | UNI 6065 | 10 |
| Carico di rottura / tensile strength | MPa | UNI 6065 | 16 |
| Allungamento a rottura / elongation at break | % | UNI 6065 | 425 |
| Perdita all'abrasione / abrasion loss | mm ³ | UNI 9185 | < 100 |
| Resa elastica / elastic yield | % | UNI 7718 | 33 |

Anima metallica / metal core

| | Um | Norme / norms | Valore / value |
|-------------------------|----|---------------|-----------------|
| Tipo / type | | | S235JR (Fe 360) |
| Dimensioni / dimensions | | | 30x30x3 |

Tabella Tolleranze / Table Tolerances

| | da / from | a / to | Um | tolleranze / tolerances |
|-------------------------------|-----------|--------|------|-------------------------|
| Durezza / hardness | - | - | SH/A | ± 5 |
| Resa elastica / elastic yield | - | - | % | ± 3 |